

ATHENS: V. MOIRA, INDUSTRIAL AREA MANDRA, 19600, ATHENS, GREECE, TEL.:+30 210 5557579, FAX: +30 210 5558482

THESSALONIKI: 10th km N.R THESSALONIKIS-POLIGIROU, 57001, THERMI THESSALONIKI, GREECE, TEL.:+30 2310 467275, FAX: 2310 463442

Betofix[®] Waterstop

Description of the product

Solvent based paint for the protection of moist surfaces.

Applications

Betofix[®] Waterstop is suitable for for the protection of moist surfaces in basements, walls, air conditioning rooms.

Properties/Advantages

- It is simple to implement and does not require special care in the preparation of the surface
- Displays excellent adhesion even on porous or alkaline substrates
- Capable of withstanding increased negative pressures
- Resistant to washing detergent
- Non-yellowing

Technical Characteristics

Density (25 ^o C)	1,42 kg/l
Flash point	+42 ^o C
Consumption	500gr/m ² for 2 coats
Drying time (25 ^o C)	4-5 hours
Ambient Temperature	From +5 ^o C to +35 ^o C
Overcoating time (25 ^o C)	24 hours

Instruction for use

Surface preparation: The substrate should be clean, dry and free from dust, oil, grease, or any poorly adhering material.

The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX[®] SA .It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX[®] SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.

Betofix[®] Waterstop

Application:

Stir the product thoroughly in its container. Apply two coats of **Betofix[®] Waterstop** by brush or roller. Dilute with solvent **Neotex 1080** (10-15%).

Notes

If there is an increased negative pressure it is recommended to apply first the cement-based brushable waterproofing system **Neopress[®]** reinforced with emulsion **Revinex[®]** by creating openings reliefs. After the closure of these openings apply **Betofix[®] Waterstop**

Colours

White

Packaging

Cans of 1kg and 5kg

Cleaning of tools

Use Solvent **Neotex 1080**

Stain removal

Use Solvent **Neotex 1080**

Storage stability

The product is stable for 2 years when kept unopened in its original container, protected from frost and direct sunlight.