

Neoproof® 360W

Water-based elastomeric waterproofing coating, for non-exposed surfaces

Fields of application

Neoproof® 360W is a brushable water-based elastomeric waterproofing coating, particularly suitable for non-exposed horizontal or vertical building surfaces prior to plastering or the application of ceramic tiles, roof tiles etc. or before laying insulating panels. Ideal for waterproofing in planter boxes.

Properties

- Forms a blister-free membrane, impermeable to moisture, providing high mechanical properties
- Excellent adhesion strength on numerous building surfaces
- Highly resistant to alkali
- Exhibits high flexural and tensile strength
- Easy to apply and dries quickly
- Offers protection against underground radon

Technical Characteristics

Density	1,32kg/L
Elongation at break (ASTM D412)	270% (±20%)
Tensile strength at break (ASTM D412)	3,5MPa (±0,2MPa)
Adhesion strength (EN 1542:2001)	> 2.5N/mm ²
Drying time (+25°C)	1-2 hours
Dry to recoat (+25°C)	24 hours
Total hardening	~7 days
Consumption	1kg/m ² for two layers (cementitious surface)

V.O.C. limit acc. to the E.U. Directive 2004/42/CE for this product of category AcWB: 40g/l (Limit 1.1.2010).

V.O.C. content of the ready to use product <40g/l.

Instruction for use

Surface preparation: The surface must be stable, clean, dry, protected from rising moisture and free from dust, grease and loose materials. Any poorly adhering materials and older coatings should be removed and the surface should be thoroughly cleaned mechanically or chemically. Depending on the substrate, appropriate mechanical preparation may be required, in order to smooth the irregularities, open the pores and create the optimum conditions for adhesion. The surfaces should be flat, smooth and

Neoproof® 360W

continuous (i.e. without holes, cracks, bays, etc.). In the opposite case, they should be treated accordingly (e.g. by proper puttying).

Priming: Prior to the application of **Neoproof® 360W**, the proper **NEOTEX®** primer should be applied, depending on the substrate. In the case of cementitious substrates, it is proposed to apply **Revinex®** diluted with water in a ratio **Revinex®:water** - 1:4 or the solvent-based primers **Silatex® Primer** or **Vinyfix® Primer**.

Application: Following the priming of the surface, **Neoproof® 360W** is applied, after thorough stirring, in at least two layers by roller, brush or airless spray. If needed, it may be diluted up to 10% with water. After applying the final layer and while it is still fresh, it is advisable to broadcast quartz sand on top of **Neoproof® 360W** so as to promote the adhesion of the subsequent tile adhesive or plaster. After 24 hours, any loose grains should be removed with a high suction vacuum cleaner.

Notes

- **Application conditions:** Surface moisture: <4%, Relative atmosphere moisture: <80%, Ambient and substrate temperature: +8°C min. / +35°C max.
- **Neoproof® 360W** should not be applied under wet conditions, or if wet conditions are expected to prevail during the curing period of the product.
- Every subsequent layer of **Neoproof® 360W** should be applied in a vertical or different direction than the previous one
- **Neoproof® 360W** should not be left exposed to solar radiation
- For demanding applications (e.g. planter boxes) or when covering cracks bigger than 1,5 mm, as well as in the walls-floor intersections, **Neoproof® 360W** should be reinforced with the specially designed non-woven polyester tissue **Neotextile®**. In such cases, at least three coats of the product are required.
- In cases of inverted roof insulation or insufficient thermal insulation, it is recommended to use appropriate roof ventilation.
- For the application of tiles on top of **Neoproof® 360W**, it is advisable to use elastic tile adhesive (C2TE S1)

Colours Light beige (RAL 1015). Other colours available upon request.

Packaging 12kg, 5kg and 1kg in plastic pails

Cleaning of tools & stain removal By water immediately after application



ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482

THESSALONIKI: Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

Neoproof[®] 360W

Storage stability

2 years, stored in its original sealed packing, in an absolutely dry place, protected from frost, humidity and exposure to sunlight.

Safety Precautions

See Safety Data Sheet.



The information supplied in this datasheet, concerning the uses and the applications of the product, is based on the experience and knowledge of NEOTEX[®] SA. It is offered as a service to designers and contractors in order to help them find potential solutions. However, as a supplier, NEOTEX[®] SA does not control the actual use of the product and therefore cannot be held responsible for the results of its use. As a result of continual technical evolution, it is up to our clients to check with our technical department that this present data sheet has not been modified by a more recent edition.