

ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482
THESSALONIKI: Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

Neotextile®

Non-woven polyester reinforcement specially designed for waterproofing systems

Fields of application

- Suitable for reinforcement of coatings such as **Neorooftm**, **Silatextm**, **Super**, **Neoprooftm PU W**, **Revinextm Roof**, **Neoprooftm PU W-40**
- Specially recommended for covering cracks and upstands
- Compatible with any building surface, including metallic, for affixing.

Properties-Advantages

- Applied easily
- It does not torn
- It does not require great consumption of coatings for its impregnation
- It increases durability and efficiency of waterproofing systems

Technical characteristics

Consumption of reinforced coatings: 1, 5 kg/m²

Properties	Test Method	Mean Values
Weight	EN ISO 9864	50gr/m ²
Thickness	EN ISO 9863/1	0,45mm
Tensile strength	EN ISO 10319	1,0 KN/m
Elongation at max. load	EN ISO 10319	≥ 50%
Static puncture resistance CBR	EN ISO 12236	150 N
Cone drop test	EN ISO 13433	>50

ATHENS: V. Moira str., P.O. Box 2315, GR 19600 Industrial Area Mandra, Athens, Greece, Tel.: +30 210 5557579, Fax: +30 210 5558482
THESSALONIKI: Ionias Str., GR 57009 Kalochori, Thessaloniki, Greece, Tel.: +30 2310 467275, Fax: +30 2310 463442

Neotextile[®]

Instruction for use	After the first layer of the coating is applied (the use of a primer is advisable for improving adhesion) place Neotextile[®] . At least two more coats are required for the complete coverage of the product.
----------------------------	--

Storage stability	Unlimited
--------------------------	-----------

Packing	Roll 300 x 1,08 m Roll 100 x 1,08 m Roll 50 x 1,08 m Tape 10m x 9 cm Tape 10m x 18 cm
----------------	---

